

## Product Data Sheet

### Eastman™ Cellulose Acetate Butyrate (CAB-381-0.5)

#### Application/Uses

- Automotive OEM
- Coatings
- Coatings for Automotive Plastics
- Coatings for plastic
- Lacquers
- Lacquers for automotive
- Nail care
- Printing Inks
- Truck/Bus/Commercial Vehicles

#### Product Description

Remarkable polymers with a renewable backbone provided by nature itself.

Eastman™ Cellulose Acetate Butyrate (CAB 381-0.5) is a cellulose ester with medium butyryl content and low viscosity. It was designed for use where low-application viscosities at relatively high solids levels is needed. It is soluble in a wide range of solvents and compatible with many other resins. It will also tolerate the use of solvent blends currently exempt from certain air pollution regulations. It is supplied as a dry, free-flowing powder. Eastman™ cellulose esters are based on up to sixty percent cellulose, one of the most abundant natural renewable resources.

#### Typical Properties

Property	Typical Value, Units
Butyryl Content	37 wt %
Acetyl Content	13 wt %
Hydroxyl Content	1.5%
Viscosity <sup>a</sup>	1.9 poise
Color <sup>b</sup>	150 ppm
Haze <sup>b</sup>	35 ppm
Acidity as Acetic Acid	0.03 wt %
Ash Content	<0.05%
Refractive Index	1.48
Heat Test @ 160°C for 8 hr	Tan melt
Melting Point	155-165°C
Specific Gravity	1.2
Wt/Vol (Cast Film)	1.2 kg/L (10.0 lb/gal)

Bulk Density	
Poured	352 kg/m <sup>3</sup> (22 lb/ft <sup>3</sup> )
Tapped	465 kg/m <sup>3</sup> (39 lb/ft <sup>3</sup> )
Dielectric Strength	787-984 kv/cm (2-2.5 kv/mil)
Glass Transition Temperature (T <sub>g</sub> )	130°C
Molecular Weight <sup>c</sup> M <sub>n</sub>	30000
Tukon Hardness	18 Knoop

<sup>a</sup> Viscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

<sup>b</sup> Determination of color and haze made on a solution of the cellulose ester dissolved in MIBK using Pt-Co color standards and Johns-Manville Celite (diatomaceous silica products) haze standards.

<sup>c</sup> Polystyrene equivalent number average molecular weight determined by gel permeation chromatography.

### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

有关技术和销售资料请向下列地址联系索取：

公司名：东莞市仁捷塑胶原料有限公司

网 址：http://www.rjplastics.com

联系人：唐先生 13509239386 QQ: 13931677

电 话：0769-33268819

传 真：0769-86999593

邮 箱：tjh@rjplastics.com

www.rjplastics.com  
东莞市仁捷塑胶原料有限公司  
财富热线：13509239386